



## Technical Data Sheet

<b>DESCRIPTION</b>	Serviwrap Outerwrap is a 0.255 mm thick, tough, conformable protective coating applied over Serviwrap and Maflowrap anti-corrosion tape to protect the integrity of the coating from damage or abrasion from handling, backfill and soil stress. The Outerwrap has a PVC carrier coated with a strong pressure sensitive adhesive. The Outerwrap can be used in both temperate and tropical climates.
<b>SUBSTRATE COMPATIBILITY</b>	Any protective coating in need of additional mechanical protection
<b>RECOMMENDED USE</b>	Ideal for protecting coatings in high soil stress areas or in the presence of rocky, abrasive backfill. Also provides UV protection for exposed pipelines.
<b>SURFACE PREPARATION</b>	None Required. The Outerwrap is a mechanical protective overwrap, not a corrosion preventative coating.
<b>SAFETY</b>	Refer to Material Safety Data Sheet: MSDS-Outerwrap
<b>APPLICATION</b>	Refer to Application Guidelines: AG-COLD-APPLIED-BITUMEN-TAPE

### TYPICAL DATA

Property	Metric	US Customary	Test Method
Color	Light Gray	Light Gray	
Total Thickness	0.255 mm	10 mil	ASTM D1000
PVC Thickness	0.23 mm	9 mil	ASTM D1000
Adhesive Thickness	0.025 mm	1 mil	ASTM D1000
Adhesion to PVC	0.39 N/mm	2.2 lbf/in	ASTM D1000
Tensile Strength	22.4 N/mm <sup>2</sup>	3236 psi	ASTM D638
Elongation	170%	170%	ASTM D638
Tear Strength	8 N/mm	45.7 lbf/in	ASTM D1004
Dielectric Strength	> 10 kV	> 10 kV	ASTM D149

### ORDERING INFORMATION

Width	Length
50, 100, 150 mm	33 m

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Protective Coatings Ltd  
Harbour Road,  
Rye, East Sussex, TN31 7TE, UK  
Phone: +44(0)1797.223561  
Fax: +44(0)1797.224530  
www.chasecorp.com  
A BS EN ISO 9001:2008  
REGISTERED COMPANY

Chase Corporation  
295 University Avenue  
Westwood, MA 02090  
Phone: 800-323-4182  
Fax: 781-332-0701  
www.chasecorp.com  
An ISO 9001:2008  
REGISTERED COMPANY