



Luja Universal Primer

DESCRIPTION

Acrylate primer

PRODUCT FEATURES

For priming and finishing concrete, filler treated, brick, cardboard, chipboard and wood fibre board surfaces. Also adheres well to previously painted clean dispersion, alkyd, epoxy and acid catalyzed paint surfaces.

RECOMMENDED USES

Interior walls and ceilings. Suitable as a primer for Luja finishing paints and Tikkurila interior acrylate paints. Also under wallpapers.



TECHNICAL DATA



Base paints	AP
Colour Range	White. Can be tinted to light shades from Tikkurila Symphony colour collection. Use only half of the colourant amount given in the formula. Colour accuracy is not perfect.
Gloss grade	Full-matt
Building material emission class	M1
Coverage	Non-absorbent surfaces 7 - 10 m ² /l. Absorbent surfaces 5 - 8 m ² /l.
Can sizes	0,9 l, 2,7 l, 9 l, 18 l.
Thinner	Water
Application method	Brush, roller or spray. For airless spray application, use a nozzle 0.015" - 0.021" Thinning: 0 - 10 vol-%
Drying time at 23°C and 50% relative air humidity	Dry to touch in half an hour. Re-coatable after 2 hours.
Wet scrub resistance	SFS-EN 13300 class II, ISO 11998
Chemical resistance	Resists cleaning detergents and weak solvents, e.g. White Spirit.
Heat resistance	85°C, ISO 4211-3.
Solids volume	36 %.
Density	1.4 kg/l, ISO 2811.
Storage	Protect from frost.
Product code	219_0201

APPLICATION DETAILS

Application conditions	The surface to be painted must be dry, the temperature of the air at least +5°C, and the relative humidity of the air below 80 %.
Preparation	Unpainted surfaces: Remove all dirt and dust. Fill the surfaces with a suitable Presto filler and sand the dried surface. Remove sanding dust. Previously painted surfaces: Wash down previously painted surfaces with Cleaning Agent (Maalipesu) and rinse carefully with water. Fill holes and cracks with a suitable Presto filler and sand the dried surface. Remove sanding dust.
Painting	Stir Luja Universal Primer well before use and thin with water, if necessary. Apply by brush, roller or spray. Finish the surface with Luja Finishing Paint, Remontti-Ässä or Ässä finishing paint.
Cleaning of tools	Clean tools with water. Use of Tikkurila Pensselipesu (Tool Cleaner) is recommended when cleaning a bit hardened paint from the brush.
Maintenance instructions	Clean the surfaces with neutral (pH 6-8) detergent with soft brush, sponge or cloth at the earliest 1 month after painting. Follow the dilution instructions of the detergent manufacturer. The surface may not remain wet after the cleaning. Be careful with the painted surfaces during few weeks time, because the paint will achieve its final hardness and durability in normal conditions after 1 month. If the surfaces must be cleansed soon after painting, cleanse them lightly with a damp cleaning cloth.
EU VOC 2004/42/EC-limit value	(cat A/g) 30g/l(2010) Luja Universal Primer contains VOC max. 30 g/l

HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

The product is not classified as dangerous. A Safety Data Sheet is available on request. [Safety data sheet](#)

ENVIRONMENTAL and WASTE DISPOSAL TRANSPORT

Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local regulations.
VAK/ADR -

ser070415 / garta181214 / pih101214 / ome040609 / 2190201

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As



Luja Universal Primer

manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

[Back](#)