

OK 67.60

Acid-rutile coated MMA-electrode giving an overalloyed weld metal. Suitable for welding stainless steel to mild and low alloyed steels. Also suitable for welding of transition layers when surfacing mild steel with stainless steel weld metal.

Specifications	
Classifications	EN ISO 3581-A : E 23 12 L R 3 2 SFA/AWS A5.4 : E309L-17 CSA W48 : E309L-17 Werkstoffnummer : 1.4332
Approvals	CE : EN 13479 CWB : E309L-17 DNV-GL : VL 309 UKCA : EN 13479 VdTÜV : 00898

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	DC+, AC
Ferrite Content	FN 10-22
Alloy Type	Austenitic CrNi
Coating Type	Acid Rutile

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
ISO			
As Welded	470 MPa	580 MPa	32 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
ISO		
As Welded	20 °C	50 J
As Welded	-10 °C	40 J

Typical Weld Metal Analysis %						
C	Mn	Si	Ni	Cr	N	Ferrite FN
0.03	0.9	0.8	12.4	23.7	0.09	15

Deposition Data					
Diameter	Current	Voltage	Efficiency (%)	Fusion time per electrode at 90% I max	Deposition Rate
2.0 x 300.0 mm	45-65 A	27 V	60 %	38 sec	0.7 kg/h
2.5 x 300.0 mm	45-90 A	28 V	60 %	38 sec	1.1 kg/h
3.2 x 350.0 mm	65-120 A	29 V	60 %	51 sec	1.6 kg/h
4.0 x 350.0 mm	85-180 A	31 V	60 %	51 sec	2.5 kg/h
5.0 x 350.0 mm	110-250 A	32 V	60 %	58 sec	3.3 kg/h