

PROTECTA® FR IPT

TECHNICAL DATA SHEET



Table of contents

Description	page 1
Features	page 1
Properties	page 1
Limitations	page 2
Pipe End Configurations	page 2
Sound Insulation	page 2
Usage	page 2
Emission Data (indoor air quality)	page 2
Air Permeability	page 3
Technical Data	page 3

For application guidance please refer to the Installation Instructions.

Description

Protecta® FR IPT is a high performance, professional quality, one part ready to use sealant and adhesive. Based on an innovative new Inert Polymer Technology it is suitable for a wide variety of building trade applications including decorating, flooring, joinery, plumbing and tiling and outperforms conventional water based products as a sealant and adhesive.

Protecta® FR IPT is designed for sealing joints, voids/irregular holes in walls, partitions and other structures, resulting in an airtight and watertight seal. IPT is a non-reactive environmentally friendly chemistry that ensures compatibility with most building materials and has the unique property of moving dynamically to accommodate the natural or unexpected movements of sealed/bonded joints within a building, for long-lasting performance.

Protecta® FR IPT eliminates the selection choices that need to be made with conventional sealants and adhesives. Choosing a product for a building application can be confusing especially as there are a wide number of products available and within those products a variety of grades, with variations in properties to suit the substrate or application. Protecta® FR IPT overcomes this by offering the tradesman one solution for all internal building applications.

Features

- Primerless adhesion
- Excellent adhesion to most common substrates
- Dynamic for low and high modulus applications
- 3D joint movement capability minimum 25%
- Can be used for all applications internally
- Fire rated up to 4 hours both integrity and insulation
- Resistant against radon (radioactive particles)
- Excellent slump resistance
- Free of VOC
- Resistant to mould and mildew
- Low dirt pick up
- Non staining on susceptible surfaces
- Easy to apply and tool off
- Excess can be wiped before curing with a damp cloth
- Paintable
- Low shrinkage
- Does not yellow



Properties

Protecta® FR IPT remains permanently flexible and is paintable with both alkylid resin and water based paints.

Suitable applications include:

- Internal sealing around doors and windows
- Sealing where air quality for health is important
- Sanitary applications including showers
- Sealing of gaps around fitted furniture and worktops
- Sealing around flooring
- Fire resistant sealing
- Radon resistant sealing
- Decorating caulking and sealing
- Air and sound sealing

Protecta® FR IPT can be used as an adhesive and has excellent initial grab quickly developing a high bond strength resulting in a permanent fixing. It is easy and economical to apply and is ideal for general construction.

IPT bonds to most building materials. Substrates include:

- Brick, concrete, stone, slate, ceramic, marble, granite
- Timber, plywood, block board, chipboard, fibreboard
- uPVC plastic trims and polycarbonate
- Insulating board
- Expanded polystyrene
- Plasterboard and plaster
- Metals, aluminium, steel, lead, copper and alloys
- Painted surfaces

Surplus uncured material can be easily removed using a damp cloth as the uncured sealant is completely soluble in water.

PROTECTA® FR IPT

TECHNICAL DATA SHEET



Limitations

- Where metals are not compatible with water contact, they should be primed prior to any sealant application.
- The sealant is soluble in water in wet/uncured state and cannot be used submerged or in rain. Applied sealant must not be sprayed with water or other fluids before skin formation (< 60 min).
- The sealant should not be used outdoors due to the design of the curing process technology, unless protected from rain and frost during cure.
- Very narrow seals cure faster than normal. There is a special version of IPT that cures more slowly.
- Recommended for use in joints up to 20mm wide, larger joints widths can be accommodated.

Pipe End Configurations

When testing pipes, one can choose not to cap (or close) the pipe, or cap the pipe inside the furnace, or outside the furnace, or on both sides. The configuration chosen depends on the intended application of the pipe and/or the installation environment.

The code defining if a pipe is capped is stated after the fire classification. For instance, EI 60 C/U which means the pipe was capped inside the furnace, and uncapped outside the furnace. The test configuration defines the approvals possible.

Our engineering judgment based on EN 1366-3:2021 are:

Intended use of pipe		Pipe end condition ³⁾
Rainwater pipe, plastic	At drainage	U/U ¹⁾
	Not at drainage	C/C ²⁾
Drainage or sewage pipe, plastic	Ventilated drain	C/U ¹⁾
	Unventilated drain	U/C ²⁾
	Drain w/water trap	U/C ¹⁾
	Not at drainage	C/C ²⁾
Metal or plastic pipe in closed system (water, gas, air etc.)		C/C ¹⁾
Metal pipe in ventilated system (sewage etc.)		U/C ¹⁾
Flue gas recovery system pipe, plastic		U/C ¹⁾
Pipe with open ends and ≥ 50cm length on both sides, plastic		U/U ²⁾
Waste disposal shaft pipe, metal		U/C ²⁾

¹⁾ Suggested in EN 1366-3:2021. ²⁾ Polyseam's judgment based on tests.

³⁾ U/U classified fire seals cover C/U, U/C and C/C. C/U classified fire seals cover U/C and C/C. U/C classified fire seals cover C/C (except steel pipes, where U/C classified fire seals cover C/U and C/C. C/U classified fire seals cover C/C).

Sound Insulation

Description	Sound reduction
Single sided seal ≥ 12mm depth	Rw 62 dB
Double sided seal ≥ 12mm depth	> Rw 62 dB

Protecta® FR IPT has been tested at EXOVA BM Trada (UKAS accredited); according to EN ISO 10140-2:2010.

Usage of any backing material is optional, due to the tests being conducted with sealant only.

Usage

Usage for a standard 300ml cartridge.

Joint size (mm)	6 x 6	9 x 6	12 x 6	25 x 10	7 x 7 fillet	10 x 10 fillet
Linear m./cartridge	8.63	5.5	4.1	1.2	12.0	6.0

Emission Data (indoor air quality)

Regulation or Protocol	Conclusion
French VOC Regulation	Pass/A+
Italian Regulation (public procurement)	Pass
German AgBB (2021)/ABG (2022)	Pass
Belgian Regulation	Pass
Blue Angel (DE-UZ 123)	Pass
BREEAM-International	Pass/Exemplary Level
BREEAM UK	Pass/Exemplary Level
BREEAM NL	Pass/Exemplary Level
BREEAM-NOR	Pass/Exemplary Level
SINTEF	Pass
Byggsvarubedomningen	Pass
DICL	Pass/Emission Class 1
WELL (EU)	Pass
LEED-EU (v4.1) BETA	Pass

Protecta® FR IPT has been tested by Normec Product Testing; reports available upon request.

PROTECTA® FR IPT

TECHNICAL DATA SHEET



Air Permeability

Positive Pressure (Pa)	Leakage (m³/h/m²)	Negative Pressure (Pa)	Leakage (m³/h/m²)
25	0.00	25	0.00
50	0.00	50	0.00
100	0.00	100	0.00
200	0.28	200	0.00
300	0.83	300	0.56
450	1.67	450	0.83
600	3.06	600	2.78

Protecta® FR IPT - tested at Warringtonfire Testing and Certification Ltd (UKAS accredited); according to EN 1026: 2016.

Technical Data

Condition	Ready to use thixotropic paste
Specific gravity	1.54 g/cm³
VOC	0 g/l
Durability w/ageing	Type X (UV / water) (pass)
Chemical resistance	Test passed (resistant)
Salt water immersion	Test passed (resistant)
Microbiologic growth	0 (no growth)
Hardness	Shore A 47
Shrinkage	15% volume single sided
Tensile properties	3.79 MPa (379 N/mm²)
Tensile elongation	270 %
3D-tensile properties	0.24 MPa (24 N/cm²)
3D-tensile elongation	106 %
Tear properties	50 %
Compression resistance	434 N / 1569 MPa
Radon resistance	1.5mm thickness IPT gives Z = 2.9 · 10⁸ s/m
Flashpoint	None
Reaction to fire	B – s1, d0
Fire resistance	Up to class EI 240
Tack free time	60 minutes maximum
Skin time	30 minutes maximum
Rate of cure	10% at 24 hours
Solids content	> 80 %
Resistance to flow	< 0.5 mm

Shelf life	Up to 12 months when stored in unopened cartridges under cool dry conditions and 6 months in opened and resealed cartridges. Avoid temperatures above 30°C & below 5°C.
Frost	Uncured sealant should not be frozen.
Thermal Conductivity	0.845 W/mK (+/- 3%) at 20mm depth (to EN 12667)
Compatibility	Can be used in contact with most building and decorating materials.
Service Temp	-40 °C to +75 °C
Classification CE	Facade (interior) 25LM Sanitary joints XS1
Colours	A range of colours are available. Standard colours are white, light grey, grey, anthracite, black and brown. Can also be overpainted
Packaging	300ml eco-foil, 300ml cartridge, 600ml foil.
Health & safety	No health hazard, approved for BREEAM rated building projects. See safety data sheet.
Test laboratories	SP Sveriges Provningsverk, SE Intertek Chemicals & Phar., GB Warringtonfire, GB Normec Product Testing, BE
Responsible	Protecta® Sealants & Adhesives manufactured by Polyseam Limited in UK Phone +44 (0)1484 421 036.

The information contained in this data sheet is given in good faith and is based on results gained from experience and tests. However all recommendations and suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the terms and conditions of sale, a copy of which is available on request.