



# PYROPLAST® TOP WB

## WATER-BASED TOPCOAT FOR FIRE PROTECTION COATINGS ON WOOD

Revised 07/2023 Issue 1

### PRODUCT DESCRIPTION

A 1-pack topcoat specially designed for Pyroplast® intumescent fire protection systems against humidity and mechanical strain.

It has no impact on the formation of the heat insulating foam of the intumescent coatings.

- Free of halogens and aromatic solvents
- Applicable on Pyroplast® Wood P intumescent coating systems for wood (level 4) of DGNB as part of the coating system

### RECOMMENDED USE

Used as topcoat on fire protected wood for weathering and / or decorative reasons.

In special conditions, e.g. frequent formation of condensation and / or heating up of surfaces above + 45°C, adequate arrangements should be taken.

In dry and clean conditions, topcoating with Pyroplast® Top WB on Pyroplast® fire protection coatings may not required.

### PRODUCT TECHNICAL DATA

**Volume Solids:** 40 ± 2 % (ISO 3233-3)

**Weight Solids:** 52 ± 2 %

**VOC:** 0 g/l determined practically in accordance with Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).  
31 g/l calculated from formulation to satisfy EC Solvent Emissions Directive.  
25 g/kg calculated from formulation to satisfy EC Solvent Emissions Directive (UK).

**Colours:** RAL colour shades

**Flash Point:** > 101°C

**Cleaner/Thinner:** Water (for cleaning)  
Thoroughly clean tools and equipment immediately after use.  
Do not thin Pyroplast® Top WB.

**Pack Size:** Single component material:  
11 kg (8.8 litre) and 3 l.  
Volume will vary with density.

**Density:** 1.25 kg/l (may vary with colours)

**Shelf Life:** 18 months from date of manufacture, stored in originally sealed containers in a cool and dry environment.  
Protect against frost.

#### Recommended Application Methods:

Airless Spray, Brush and Roller

#### Typical Thickness:

##### Recommended Spreading Rate Per Coat

	Typical
Dry	50 µm
Wet	96 µm
Theoretical Consumption*	0.120 kg/m <sup>2</sup> 0.096 l/m <sup>2</sup>
Theoretical Coverage*	8.32 m <sup>2</sup> /kg 10.40 m <sup>2</sup> /l

\* This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment.

Due to an unleaded and unchromated pigment coating, a higher loading of 200 g/m<sup>2</sup> (0.160 l/m<sup>2</sup>) is required in several work steps to reach the designated opacity.



# PYROPLAST® TOP WB

## WATER-BASED TOPCOAT FOR FIRE PROTECTION COATINGS ON WOOD

Revised 07/2023 Issue 1

### AVERAGE DRYING TIMES

#### For 50 µm Dry Film Thickness:

	+ 20°C and 60% RH
Dry to touch	30 min
Dry to handle	6 hours
To recoat	6 hours

A complete drying of the fire protection coating prior topcoat application is highly recommended.

Through-drying of the used Pyroplast® intumescent coating can be checked by 'finger-nail-test'.

Final cure: Approx. 24 hours after application at + 20°C object temperature and 60 % relative humidity.

These figures are given as a guide only. Factors such as air movement, film thickness and humidity must also be considered.

### APPROVALS & ENDORSEMENTS

#### Sustainability:

- Complies with German AgBB and French VOC (A+) when uses as part of the coating system.

### SURFACE PREPARATION

Prior application of the topcoat, the surface to be coated must be dry, clean and free from dirt, oil, grease or any other contamination.

### MIXING

The material is supplied ready for use; stir thoroughly with a mechanical paint mixer prior to application.

During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

### APPLICATION CONDITIONS

Substrate temperature shall be between + 5°C and + 40°C\* and at least 3°C above the dew point.

Material temperature shall be above + 15°C

Relative air humidity shall be below 80%.

During application and drying of total Pyroplast® intumescent coating system including Pyroplast® Top WB as well as transportation special protection measures must be taken against weathering.

Note: With critical situations e.g. frequent formation of condensation and / or heating up of surfaces above + 45°C, adequate arrangements should be taken.

\* If higher temperatures occur, please consult Sherwin-Williams for further assistance.

### APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for satisfactory application characteristics. Always purge spray equipment before use with listed cleaner (water).

#### Airless Spray

Unit: Efficient airless equipment (pressure ratio > 30: 1)

Tip Size: 0.28 – 0.38 mm (0.011 – 0.015 inch)

Fan Angle: 40° - 80°

Operating Pressure: min. 180 bar (2600 psi)

Spray hoses: Ø ¼ inch (6 mm)

Hoses must be used for water-based products only.

Material shall be applied undiluted.

The airless spray details given above are intended as a guide only.

Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent satisfactory atomisation.

As conditions will vary from job to job, it is the applicators responsibility to ensure that the equipment in use has been set up to give the best results.

If in doubt consult Sherwin-Williams customer service.

#### Brush and Roller

- Material shall be applied undiluted
- Load natural fine bristle brushes or short pile lambswool rollers are recommended

### RECOMMENDED SYSTEMS

#### Wood

Surface and / or primer:

See corresponding product data sheet of the Pyroplast® intumescent coating range

Intumescent coating:

Pyroplast® Wood P

Topcoat:

Pyroplast® Top WB



# PYROPLAST® TOP WB

## WATER-BASED TOPCOAT FOR FIRE PROTECTION COATINGS ON WOOD

Revised 07/2023 Issue 1

### HEALTH & SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

### WARRANTY

Whilst all statements made about our products (whether in this data sheet or otherwise) are correct and accurate to the best of our knowledge, we have no control over the quality or the condition of the substrate, the application conditions or the many other factors affecting your use and application of our product.

The appropriateness of the product under the actual conditions of application or intended use must be determined exclusively by you. The content of this document, and of any oral or written statements already made or to be made in relation to the subject matter of this document, including any suggestions as to appropriate products and any proposed application methods, technical details and other product information represent only test results or experience obtained under controlled or defined circumstances, and is therefore provided for general information purposes only.

Unless we agree specifically in writing to do so, we will not be liable to you for any loss or damage whether in contract, tort (including negligence), breach of statutory duty, misrepresentation, misstatement or otherwise, arising under or in connection with this document or such statements.

We disclaim any express or implied representations, warranties or guarantees (including any implied warranty of merchantability or fitness for a particular purpose), though nothing in this disclaimer excludes or limits our liability for death or personal injury arising from our negligence, or our fraud or fraudulent misrepresentation, or any other liability that cannot be excluded or limited by law.

All products supplied and technical advice given are subject to our Standard Terms and Conditions of Sale which you should request a copy of and review carefully.

This document may be modified and updated from time to time, and is uncontrolled once printed. It is the users responsibility to ensure they are using the most up to date version – this can be found at: [www.sherwin-williams.com/protectiveEMEA](http://www.sherwin-williams.com/protectiveEMEA).

If this datasheet has been translated, then it has been done using the English version as the source. In case of any queries, please refer to the master English version which can be found at: [www.sherwin-williams.com/protectiveEMEA](http://www.sherwin-williams.com/protectiveEMEA).