



AURORA WINTER

With its dichroic and chameleon-like properties, the self-adhesive Aurora film changes in hue and colour with every variation in angle of observation.

The Aurora decorative film uses natural light to maximum effect, bringing your windows and glass partitions to life through its warm tones dichroic tint.



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

TECHNICAL DATA

Data calculated based on film applied to clear glass 3 mm thick (* on double glazing 4-16-4)

Ultraviolet transmission	10%
Visible light transmission	72%
Reflection of external visible light	10%
Reflection of internal visible light	10%
Total solar energy rejected	39%
Total solar energy rejected 2 *	34%
Solar ratio:	
Solar energy reflection	0%
Solar energy absorption	0%
Solar energy transmission	0%
Reduction in Solar Glare	28%
G-value	NC
U-value	NC
Shading coefficient	NC
Installation type	Interior
Roll length	30,5 m
Film composition	PET
Thickness	55 µ
Colour from the outside	Cold colors

MAINTENANCE

Use soapy water solution for cleaning. Do not clean for at least a month after installation and do not apply any type of stickers or adhesive on the film. For more information read our maintenance instructions and quality standards on www.solfilmsgrossisten.se

INSTALLATION ADVICE

Vertical installation and on standard glass surface *

Clear single pane	✓
Tinted single pane	!
Reflective tinted single pane	✓
Clear double pane	!
Tinted double pane	!
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	!
STADIP INT. clear double pane	✗

✓ Yes ! Caution ✗ Not

Recommended

* Recommendations provided on the basis of a glazed surface covering up to 2.5 m², contact us for definitive details or to obtain a thermal shock analysis report.

CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation

