




BLACK PLUS 10

With its well-appointed design, the Black Plus 10 automotive film combines discretion and privacy from prying eyes with technical efficiency in reflecting solar heat.



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

TECHNICAL DATA

Data calculated based on film applied to clear glass 3 mm thick (* on double glazing 4-16-4)

Ultraviolet transmission	1%
Visible light transmission	12%
Reflection of external visible light	6%
Reflection of internal visible light	6%
Total solar energy rejected	47%
Total solar energy rejected 2 *	40%
Solar ratio:	
Solar energy reflection	8%
Solar energy absorption	42%
Solar energy transmission	34%
Reduction in Solar Glare	85%
G-value	NC
Installation type	Interior
Roll length	30,5 m
Film composition	PET
Thickness	40 µ
Colour from the outside	Black

MAINTENANCE

Use soapy water solution for cleaning. Do not clean for at least a month after installation and do not apply any type of stickers or adhesive on the film. For more information read our maintenance instructions and quality standards on www.solfilmsgrossisten.se

INSTALLATION ADVICE

Vertical installation and on standard glass surface *

Clear single pane	✓
Tinted single pane	✗
Reflective tinted single pane	✗
Clear double pane	✗
Tinted double pane	✗
Reflective tinted double pane	✗
Gas-filled double pane - Low E	✗
STADIP EXT. clear double pane	✗
STADIP INT. clear double pane	✗

✓ Yes ! Caution ✗ Not

Recommended

* Recommendations provided on the basis of a glazed surface covering up to 2.5 m², contact us for definitive details or to obtain a thermal chock analysis report.

CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester with optical distortion
3. Bonding adhesive
4. High optical quality polyester with anti-heat IR particles
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation

