



CLEAR 17 C

Clear 17 C film helps secure your windows by ensuring that the glass does not shatter, remaining transparent and retaining its overall integrity in the event of an impact, explosion or fire. Ideally suited to covering large glazed expanses, it complies with European Standard EN 13541-ER1.



Fire-resistance rating



Storage from -5°C to +40°C
3 YEARS



European Standard EN 13541
ER1



REACH RoHS compliant
RESPECTED

TECHNICAL DATA

Data calculated based on film applied to clear glass 3 mm thick (* on double glazing 4-16-4)

| | |
|--------------------------------------|-------------|
| Ultraviolet transmission | 1% |
| Visible light transmission | 86% |
| Reflection of external visible light | 12% |
| Reflection of internal visible light | 12% |
| Total solar energy rejected | 20% |
| Total solar energy rejected 2 * | 21% |
| Solar ratio: | |
| Solar energy reflection | 10% |
| Solar energy absorption | 9% |
| Solar energy transmission | 81% |
| Reduction in Solar Glare | 16% |
| G-value | 0.80 |
| U-value | 5.7 |
| Shading coefficient | 0.9 |
| Installation type | Interior |
| Roll length | 30,5 m |
| Film composition | PET |
| Thickness | 485 µ |
| Colour from the outside | Transparent |

MAINTENANCE

Use soapy water solution for cleaning. Do not clean for at least a month after installation and do not apply any type of stickers or adhesive on the film. For more information read our maintenance instructions and quality standards on www.solfilmsgrossisten.se

INSTALLATION ADVICE

Vertical installation and on standard glass surface *

| | |
|--------------------------------|---|
| Clear single pane | ✓ |
| Tinted single pane | ✓ |
| Reflective tinted single pane | ✓ |
| Clear double pane | ✓ |
| Tinted double pane | ✓ |
| Reflective tinted double pane | ✓ |
| Gas-filled double pane - Low E | ✓ |
| STADIP EXT. clear double pane | ✓ |
| STADIP INT. clear double pane | ✓ |

✓ Yes ! Caution ✗ Not

Recommended

* Recommendations provided on the basis of a glazed surface covering up to 2.5 m².

CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. 100µ high optical quality polyester
3. Adhesive bonding layer
4. 100µ high optical quality polyester
5. Non permanent PS adhesive
6. 100µ high optical quality polyester
7. Adhesive bonding layer
8. 100µ high optical quality polyester
9. Reinforced PS adhesive to support the film's elasticity in case of impact, polymerizing with the glass within a 30-day timeframe.
10. Protection release liner, disposable after installation