



CLEAR 4 XC G

Clear 4 XC G solvent resistant films provide highly effective protection against tags and graffiti. Its protective qualities are not limited to solvents, it will also shield a window's surface from other acts of vandalism involving scratching or acid etching. An easy film to install and replace, it is also classed as a security film, providing protection by holding shattered glass in place in the event of an explosion or serious impact.



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



European Standard EN 12600
2B2



REACH RoHS compliant
RESPECTED

TECHNICAL DATA

Data calculated based on film applied to clear glass 3 mm thick (* on double glazing 4-16-4)

Ultraviolet transmission	1%
Visible light transmission	93%
Reflection of external visible light	9%
Reflection of internal visible light	9%
Total solar energy rejected	17%
Total solar energy rejected 2 *	18%
Solar ratio:	
Solar energy reflection	10%
Solar energy absorption	8%
Solar energy transmission	82%
Reduction in Solar Glare	14%
G-value	0.83
U-value	5.7
Shading coefficient	0.9
Tensile strength (kg/cm ²)	28
Elongation at break	125%
Installation type	Exterior
Roll length	30,5 m
Film composition	PET
Thickness	125 µ
Colour from the outside	Transparent

MAINTENANCE

Use soapy water solution for cleaning. Do not clean for at least a month after installation and do not apply any type of stickers or adhesive on the film. For more information read our maintenance instructions and quality standards on www.solfilmsgrossisten.se

INSTALLATION ADVICE

Vertical installation and on standard glass surface *

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	✓

✓ Yes ! Caution ✗ Not

Recommended

* Recommendations provided on the basis of a glazed surface covering up to 2.5 m².

CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation

