

# SILVER 01 INT INTERIOR SOLAR CONTROL FILMS



## **SILVER 01 INT**

Silver 01 INT films are highly effective at reducing solar heat gain. Solar glare is greatly diminished and its one-way mirror aspect guarantees privacy from prying eyes, whilst affording a modern feel to the exterior of a building.





 $\bowtie$ 

Fire-resistance rating

Storage from -5°C to +40°C 3 YEARS

REACH RoHS compliant RESPECTED

### **TECHNICAL DATA**

Data calculated based on film applied to clear glass 3 mm thick (\* on double glazing 4-16-4)

Ultraviolet transmission	<1%
Visible light transmission	0.5%
Reflection of external visible light	82%
Reflection of internal visible light	82%
Total solar energy rejected	91%
Total solar energy rejected 2 *	88%
Solar ratio:	
Solar energy reflection	78%
Solar energy absorption	18%
Solar energy transmission	4%
Reduction in Solar Glare	99%
G-value	0.09
U-value	5.1
Shading coefficient	0.10
Installation type	Interior
Roll length	30,5 m
Film composition	PET
Thickness	60 µ
Colour from the outside	Silver

### MAINTENANCE

Use soapy water solution for cleaning. Do not clean for at least a month after installation and do not apply any type of stickers or adhesive on the film. For more information read our maintenance instructions and quality standards on www.solfilmsgrossisten.se

#### **INSTALLATION ADVICE**

Vertical installation and on standard glass surface \*

Clear single pane	$\checkmark$
Tinted single pane	1
Reflective tinted single pane	$\sim$
Clear double pane	
Tinted double pane	×
Reflective tinted double pane	~
Gas-filled double pane - Low E	×
STADIP EXT. clear double pane	×
STADIP INT. clear double pane	×

### ✓ Yes Caution X Not

#### Recommended

\* Recommendations provided on the basis of a glazed surface covering up to 2.5 m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.

#### CONSTRUCTION

- 1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
- 2. High optical quality polyester, with anti IR metal particles deposit
- 3. Bonding adhesive
- 4. High optical quality polyester
- **5.** PS adhesive, glass polymerization within 15 days
- 6. Protection release liner, disposable after installation

